


Q Search...



*Silver-Line Plastics*

(/)



Home (/) ▶ Products By Type (/products-by-type/) ▶ CPVC (/products-by-type/cpvc) ▶ Ultra-Pure® CPVC

## ULTRA-PURE® CPVC

Ultra-Pure® CPVC Hot-and-Cold Water Tubing

Silver-Line's Ultra-Pure® CPVC pipe meets / exceeds FlowGuard Gold materials

CPVC does not corrode or accumulate mineral deposits

- ✓ CPVC SDR 11 CTS - 10 ft.
- ✓ CPVC SDR 11 CTS - 20 ft.

---

### **CPVC SDR 11**

#### Standard Compliances:

- ASTM D-2846, standard for CPVC hot and cold water distribution (NSF®-pw-G)

Material complies with ANSI / NSF® Standard 14 & 61

Meets the requirements of FHA Use of Materials Bulletin 76 (link to bulletin ([http://portal.hud.gov/hudportal/documents/huddoc?id=DOC\\_19581.pdf](http://portal.hud.gov/hudportal/documents/huddoc?id=DOC_19581.pdf)))

Meets the 25/50 flame spread and smoke development requirement for plenum applications. Ref: ICC-ES PMG-1323 tested per ASTM E 84 (link to ICC-ES PMG Listing ([http://www.icc-es-pmg.org/Listing\\_Directory/pdf/PMG-1323.pdf](http://www.icc-es-pmg.org/Listing_Directory/pdf/PMG-1323.pdf)))

---

CPVC SDR 11 CTS - 10 FT.

<b>Nominal Size</b>	<b>Item Number</b>	<b>Outside Diameter</b>	<b>Min. Wall Thickness</b>	<b>Inside Diameter (Value)</b>	<b>Max Working Pressure at 73° F</b>	<b>Max Working Pressure at 180° F</b>	<b>Wt/100'</b>	<b>Ft/Pallet</b>
1/2"	37.051	0.625	0.060	0.484	400 PSI	100 PSI	8	12,000
3/4"	37.071	0.875	0.080	0.688	400 PSI	100 PSI	16	6,000
1"	37.101	1.125	0.102	0.888	400 PSI	100 PSI	25	4,000
1-1/4"	37.121	1.375	0.125	1.094	400 PSI	100 PSI	37	1,000
1-1/2"	37.151	1.625	0.148	1.296	400 PSI	100 PSI	51	1,000
2"	37.201	2.125	0.193	1.703	400 PSI	100 PSI	86	400

Swipe to see more...

### CPVC SDR 11 CTS - 20 FT.

<b>Nominal Size</b>	<b>Item Number</b>	<b>Outside Diameter</b>	<b>Min. Wall Thickness</b>	<b>Inside Diameter (Value)</b>	<b>Max Working Pressure at 73° F</b>	<b>Max Working Pressure at 180° F</b>	<b>Wt/100'</b>	<b>Ft/Pallet</b>
1/2"	37.052	0.625	0.060	0.484	400 PSI	100 PSI	8	24,000
3/4"	37.072	0.875	0.080	0.688	400 PSI	100 PSI	16	12,000
1"	37.102	1.125	0.102	0.888	400 PSI	100 PSI	25	8,000
1-1/4"	37.122	1.375	0.125	1.094	400 PSI	100 PSI	37	2,000
1-1/2"	37.152	1.625	0.148	1.296	400 PSI	100 PSI	51	2,000
2"	37.202	2.125	0.193	1.703	400 PSI	100 PSI	86	800

Swipe to see more...

\*See more information in technical section

## INDUSTRY ORGANIZATION AFFILIATIONS & BUYING GROUP MEMBERSHIPS



North Carolina Office 800-438-9020 (tel:8004389020)

Florida Office 877-335-9770 (tel:8773359770)

Oklahoma Office 877-300-8625 (tel:8773008625)



(<https://www.linkedin.com/company/s>

line-

© 1962 - 2019 Silver-Line Plastics | [plastics](#))